

**Description**

PG(CAN) 75W-140 SYD GO 5G

<b>Inspection Information</b>	<b>Test Method</b>	<b>Typical Value</b>
Gravity, °API	ASTM D287	34
Specific Gravity at 60°F (15.6°C)	ASTM D4052	0.855
Flash Point, °C	ASTM D92	230
Flash Point, °F	ASTM D92	446
Viscosity at 40°C, cSt	ASTM D445	171.8
Viscosity at 100°C, cSt	ASTM D445	27.64
Viscosity Index	ASTM D2270	200
Pour Point, °C (°F)	ASTM D5950	-51°C (-60°F)
Brookfield Viscosity at -40°C, cP	ASTM D2983	127,000
Color	ASTM D1500	1

## Claims Information

AGMA 9005-E02, 250.03, 250.04, 251.02, No. 4	Recommended For
AIST/US Steel 224	Recommended For
API GL-5	Recommended For
ArvinMeritor 076	Recommended For
Ford M2C108C	Recommended For
Ford M2C192-A	Recommended For
Limited Slip	Recommended For
Mack GO-J, GO-H, GO-G	Recommended For
MT-1	Recommended For
SAE J2360, MIL-2105E/F	Recommended For