

**Description**

PG(CAN) 10W-30 330GL

<b>Inspection Information</b>	<b>Test Method</b>	<b>Typical Value</b>
Gravity, °API	ASTM D287	31.63
Specific Gravity at 60°F (15.6°C)	ASTM D4052	0.8674
Flash Point, °C	ASTM D92	220
Flash Point, °F	ASTM D92	428
Viscosity at 40°C, cSt	ASTM D445	68.6
Viscosity at 100°C, cSt	ASTM D445	10.39
Viscosity Index	ASTM D2270	138
Pour Point, °C (°F)	ASTM D5950	-42°C (-44°F)
Cold Cranking Simulator at (°C), cP	ASTM D5293	5250 (-25)
High Temperature / High Shear Vis at 150°C, cP	ASTM D5481	3.12
Noack Volatility, % loss	ASTM D5800	12.3
Color	ASTM D1500	3
Zinc, wt. %	ASTM D5185	0.07
Phosphorus, wt. %	ASTM D5185	0.064
Calcium, wt. %	ASTM D5185	0.119
Sulfur, wt. %	ASTM D4951	0.235
Magnesium, wt. %	ASTM D5185	0.038
Boron, wt. %	ASTM D5185	0.007
Molybdenum, wt. %	ASTM D5185	0.004
Sulfated Ash, wt. %	ASTM D874	0.712
Nitrogen, wt. %	ASTM D4629	0.081
Pumping Viscosity at (°C), cP	ASTM D4684	19,100 (-30)
Shear Stability, Final Viscosity in cSt	ASTM D6278	8.74
Foam Seq. I (Tendency/Stability), mL	ASTM D892 (Opt. A)	0/0
Foam Seq. II (Tendency/Stability), mL	ASTM D892 (Opt. A)	0/0
Foam Seq. III (Tendency/Stability), mL	ASTM D892 (Opt. A)	0/0
High Temperature Foaming, static foam	ASTM D6082 (Opt A)	10/0
TBN, mgKOH/g	ASTM D2896	7

## Claims Information

API SJ, SH, SG, SF, SE, SD, SC	Recommended For
API SL	Recommended For
API SM	Recommended For
API SN	Recommended For
API SN PLUS	Recommended For
API SP	Approved
Chrysler MS-6395	Recommended For
GM 6094M	Recommended For
ILSAC GF-4, GF-3, GF-2, GF-1	Recommended For
ILSAC GF-5	Recommended For
ILSAC GF-6A	Approved