

Previous Name: Shell SRS 2000 Grease Summer

# Shell Gadus S4 V600AC 1.5

- Heavy Duty Protection
- Water resistant
- Red Lithium/Calcium

## Advanced Multi-purpose Heavy Duty Grease

Shell Gadus S4 V600AC provides outstanding heavy duty water resistant protection. This semi synthetic grease is the benchmark for performance in this severe service area because of the unique combination of thickener, polymers and additives.

### **DESIGNED TO MEET CHALLENGES**

#### Performance, Features & Benefits

 High base oil viscosity to provide excellent load carrying performance

Meets the recommended base oil viscosity recommended by leading OEMs.

· Excellent mechanical stability

To prevent grease breakdown, even in the presence of water.

· Excellent water resistance

Ensures lasting protection even in the presence of large amounts of water.

· Effective corrosion protection

Ensures components/bearings do not fail due to corrosion.

• Excellent Adhesion (Tackiness)

Stays in place for longer re-lubrication intervals.

#### **Main Applications**









- Shell Gadus S4 V600AC resists water and provides long lasting protection for pins, bushings, 5th wheels, chassis points, universal joints, and couplings.
- Mining
- Steel
- Forestry & Agriculture

## Specifications, Approvals & Recommendations

For a full listing of equipment approvals and recommendations, please consult your local Shell Technical Helpdesk.

### **Typical Physical Characteristics**

| Properties                                                |        |     | Method            | Shell Gadus S4 V600AC 1.5 |
|-----------------------------------------------------------|--------|-----|-------------------|---------------------------|
| NLGI Grade                                                |        |     |                   | 1.5                       |
| Color                                                     |        |     |                   | Red                       |
| Appearance                                                |        |     |                   | Tacky                     |
| Thickener                                                 |        |     |                   | Lithium/Calcium           |
| Worked Penetration - 60 strokes                           | @25°C  |     | IP 50 / ASTM D217 | 305                       |
| Worked Penetration - 100,000 strokes                      | @25°C  |     | IP 50 / ASTM D217 | 318                       |
| Worked Penetration - 100,000 strokes with 10% water added | @25°C  |     | IP 50 / ASTM D217 | 340                       |
| Estimated Operating Range Temperature                     |        | °C  |                   | -15 to 135                |
| Minimum Dispensing Temperature                            |        | °C  |                   | 0                         |
| Dropping Point                                            |        | °C  | IP 396            | 183                       |
| Base Oil Viscosity, Blended                               | @40°C  | cSt | IP 71 / ASTM D445 | 171                       |
| Base Oil Viscosity, Extracted                             | @40°C  | cSt | IP 71 / ASTM D445 | 600                       |
| Base Oil Viscosity, Extracted                             | @100°C | cSt | IP 71 / ASTM D445 | 37.2                      |
| EP Tests - 4 Ball Scar                                    |        | mm  |                   | 0.5                       |

| Properties                           |          |       | Method | Shell Gadus S4 V600AC 1.5 |
|--------------------------------------|----------|-------|--------|---------------------------|
| EP Tests - 4 Ball, Load Wear Index   |          |       |        | 50                        |
| EP Tests - Timken OK Load            |          | kg    |        | 18.2                      |
| Water Spray off, % loss              |          |       |        | 50                        |
| Water Washout Test wt % loss         | @78°C    |       |        | 5                         |
| Bomb Oxidation Pressure drop at 100h | @99°C    | kPa   |        | 20                        |
| Corrosion Test, 48 hr Rating         | @52°C    |       |        | Pass                      |
| Oil Separation, wt%                  |          |       |        | 0.3                       |
| Mobility                             | @-17.8°C | g/min |        | 0.8                       |

These characteristics are typical of current production. While future production will conform to Shell's specification, variations in these characteristics may occur.

#### Health, Safety & Environment

#### · Health and Safety

Shell Gadus S4 V600AC is unlikely to present any significant health or safety hazard when properly used in the recommended application and good standards of personal hygiene are maintained.

Avoid contact with skin. Use impervious gloves with used oil. After skin contact, wash immediately with soap and water.

Guidance on Health and Safety is available on the appropriate Material Safety Data Sheet, which can be obtained from http://www.epc.Shell.com/

#### • Protect the Environment

Take used oil to an authorized collection point. Do not discharge into drains, soil or water.

### **Additional Information**

#### · Re-greasing Intervals

For bearings operating near their maximum recommended temperatures, re-greasing intervals should be reviewed

#### Advice

Product recommendations on applications not listed here may be obtained from your Shell representative.